



Specification for

**Bitumen-based  
coatings for cold  
application, suitable  
for use in contact with  
potable water**

# Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Pigments, Paints and Varnishes Standards Policy Committee (PVC/-) to Technical Committee PVC/27, upon which the following bodies were represented:

Aluminium Federation  
 Aluminium Finishing Association  
 Aluminium Window Association  
 British Railways Board  
 British Telecommunications plc  
 Consumer Policy Committee of BSI  
 Department of the Environment (Building Research Establishment)  
 European Resin Manufacturers' Association  
 Institute of Corrosion  
 Institute of Metal Finishing  
 Institution of Structural Engineers  
 Institution of Water and Environmental Management (IWEM)  
 London Regional Transport  
 Metcom  
 Ministry of Defence  
 National Federation of Painting and Decorating Contractors  
 Oil and Colour Chemists' Association  
 Paint Research Association  
 Paintmakers' Association of Great Britain Ltd.  
 Society of Chemical Industry  
 Steel Window Association  
 Union of Construction, Allied Trades and Technicians  
 Zinc Development Association

This British Standard, having been prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 31 October 1991

© BSI 02-1999

First published October 1961  
 Second edition January 1973  
 Third edition December 1988  
 Fourth edition October 1991

The following BSI references relate to the work on this standard:  
 Committee reference PVC/27  
 Draft for comment 91/51890 DC

ISBN 0 580 20006 X

## Amendments issued since publication

Amd. No.	Date	Comments
7288	September 1992	Indicated by a sideline in the margin

# Contents

	Page
Committees responsible	Inside front cover
Foreword	ii
<hr/>	
1 Scope	1
2 Definitions	1
3 Classification	1
4 Sampling	1
5 Flash point	1
6 Drying and over-coating times	1
7 Finish	1
8 Protection against corrosion	2
9 Bend resistance	2
10 Effect on potable water	2
11 Shelf life	2
12 Marking	2
<hr/>	
Appendix A Guidance on the use of bitumen-based coatings for cold application	3
Appendix B Methods of test for performance requirements	4
Appendix C Preparation and coating of test panels	5
<hr/>	
Publication(s) referred to	Inside back cover
<hr/>	

# Foreword

This British Standard was prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee. It supersedes BS 3416:1988, which is withdrawn.

This edition introduces technical changes but it does not reflect a full review or revision of the standard, which will be undertaken in due course.

The main technical changes are:

- a) introduction of separate immersion periods for type 1 and type 2 materials;
- b) a change in the size of the panel used in Appendix B.

NOTE Differences in the text between this edition and BS 3416:1988 are indicated by a line in the margin.

This edition includes provisions to satisfy the requirements of EEC Directive 80/778/EEC "The quality of water intended for human consumption" which specifies admissible concentrations and guide levels for a wide range of parameters in respect of all drinking water and water used in food and drink manufacture. It applies to the water at the point where it is made available to the user. Compliance with the EEC Directive is required by UK law.

The statutory water supplier has a responsibility to ensure that the components of the water service connected to the water supply do not adversely affect the quality of the water supplied if that water is likely to be ingested or could be back siphoned into a part of the service from which it is likely to be ingested. The various water authorities will therefore require evidence that bitumen-based coatings in contact with potable water are satisfactory in this respect.

All types and classes of bitumen-based coatings in BS 3416 give films that are suitable for use in contact with potable water and that may be submitted for approval by the UK Water Fittings Byelaws Scheme administered by the Water Research Centre, 660 Ajax Avenue, Slough, Berkshire SL1 4BG.

This British Standard also takes account of recent developments in this type of paint enabling the use of mineral fillers and alternative solvents.

This British Standard specifies requirements for two types of bitumen coatings for cold application, each type having three classes relating to the solvent system used for the solution.

Attention is drawn to BS 6949, which specifies requirements for bitumen-based coatings not intended for use in contact with potable water.

Guidance on the use of these materials is given in Appendix A, and reference should also be made to BS 5493 and to BS 6150.

*Product certification.* Attention is drawn to the fact that bitumen-based coatings for use in contact with potable water must be certified by the Water Research Centre under the UK Water Fittings Byelaws Scheme in order to comply with EEC Directive 80/778/EEC. For full details, apply to the Water Research Centre, 660 Ajax Avenue, Slough, Berkshire SL1 4BG.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

## Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 6, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

## 1 Scope

This British Standard specifies performance and marking requirements for a range of bitumen-based solvent-borne coatings. It covers coatings for cold application by either brushing, spraying, rolling or dipping processes intended to give a coat for the corrosion protection and water-proofing of substrates including iron and steel.

Two types, each with three classes, are included. All of these give films that are suitable for use on potable water tanks and cisterns as well as for general applications.

The level of gloss of the finished film is not specified in this British Standard.

**NOTE 1** These bitumen coatings are neither intended to withstand hot conditions, as on boilers, smoke stacks, etc., for which special coatings should be obtained, nor to resist contamination with mineral oils or paint solvents, all of which conditions will cause softening of the film.

**NOTE 2** Guidance on the use of bitumen-based coatings is given in Appendix A, BS 5493 and BS 6150.

**NOTE 3** The titles of the publications referred to in this standard are listed on the inside back cover.

## 2 Definitions

For the purposes of this British Standard, the definitions given in BS 2015 apply together with the following.

### 2.1

#### bitumen

a viscous liquid, or a solid, consisting essentially of hydrocarbons and their derivatives, which is soluble in trichloroethylene and is substantially non-volatile and softens gradually when heated. It is black or brown in colour and possesses waterproofing and adhesive properties. It is obtained by refinery processes from petroleum, and is also found as a natural deposit or as a component of naturally occurring asphalt in which it is associated with mineral matter

**NOTE** The international definition of bitumen relates its solubility to carbon disulphide but, in the United Kingdom, the safer material trichloroethylene is used as the test solvent as examination has shown no significant difference.

### 2.2

#### bitumen-based coating

a liquid mixture of bitumen in a carrier (solvent or solvent mixture), usually paraffinic hydrocarbons, chlorinated hydrocarbons and aromatic hydrocarbons, with or without fillers, to give a consistency suitable for brushing, spraying, rolling or dipping in accordance with the recommendations of the manufacturer. The coating may exhibit thixotropy

## 3 Classification

**3.1** Bitumen-based coatings shall be classified into two types as follows.

- a) Type 1, without fillers.
- b) Type 2, with fillers.

**3.2** Each type shall be further sub-classified as follows.

- a) Class A, using white spirit complying with BS 245 as the carrier.
- b) Class B, using either a solvent other than white spirit, or a solvent mixture with a flash point of or above 21 °C and below 32 °C as the carrier.
- c) Class C, using either a solvent other than white spirit, or a solvent mixture with a flash point of or above 32 °C as the carrier.

## 4 Sampling

Take and store in accordance with BS 3900-A1 representative samples of not less than 1 000 mL of the coating either at the filling stage or from one or more previously unopened containers. Condition the samples for at least 12 h at  $23 \pm 2$  °C before carrying out any tests.

## 5 Flash point

When tested in accordance with **B.1**, coatings shall comply with the following.

- a) Coatings of classes A and C shall not flash at a temperature below 32 °C.
- b) Coatings of class B shall not flash at a temperature below 21 °C.

## 6 Drying and over-coating times

### 6.1 Surface-dry time

When tested in accordance with **B.2.1**, films of coatings shall be surface dry:

- a) if type 1, in not more than 4 h;
- b) if type 2, in not more than 8 h.

### 6.2 Over-coating time

When tested in accordance with **B.2.2**, the film shall show no cissing, crawling, sinking, lifting or wrinkling during application or after 24 h drying time.

## 7 Finish

When tested in accordance with **B.3**, the film shall be smooth, opaque and free from sags or runs or other surface imperfections.

## 8 Protection against corrosion

### 8.1 Resistance to tap water immersion

8.1.1 When tested in accordance with B.4.1.1, the film shall remain completely adherent to the substrate.

Any blistering shall not exceed rating 2 (S3) in accordance with BS 3900-H2.

8.1.2 When tested in accordance with B.4.1.2, the surface of exposed metal revealed shall show no visible rust or pitting.

### 8.2 Resistance to artificial sea water immersion

8.2.1 When tested in accordance with B.4.2.1, the film shall show no signs of breakdown. Any blistering shall not exceed rating 2 (S3) in accordance with BS 3900-H2.

8.2.2 When tested in accordance with B.4.2.2, the surface of exposed metal revealed shall show no visible rust or pitting.

## 9 Bend resistance

When tested in accordance with B.5, the film shall show no signs of cracking or of becoming detached from the substrate.

## 10 Effect on potable water

A coating of the product applied and left to dry in accordance with the manufacturer's instructions shall comply with BS 6920-1:1988.

## 11 Shelf life

The product, if stored in unopened containers for 12 months at a temperature not exceeding 30 °C, shall meet the requirements of clauses 5 to 9. No separation shall take place which cannot be removed by stirring.

NOTE In the case of thixotropic coatings, sufficient time, as advised by the manufacturer, should be allowed after any stirring to redevelop the thixotropy.

## 12 Marking

Each container of bitumen-based coating shall be clearly labelled with the following information:

- a) the manufacturer's identification;
- b) the number of this British Standard and the appropriate type and class of the product, e.g. BS 3416:1991<sup>1)</sup>, type 1, class A;
- c) a statement that it is suitable for use in contact with potable water;
- d) the nominal content by mass or volume;
- e) the batch number from which the container was filled;
- f) the month and year in which the batch was manufactured;
- g) whether the coating is suitable for brushing, spraying, rolling or dipping.

<sup>1)</sup> Marking BS 3416:1991 on or in relation to a product represents a manufacturer's declaration of conformity, i.e. a claim by or on behalf of the manufacturer that the product meets the requirements of the standard. The accuracy of such a claim is therefore solely the responsibility of the person making the claim. Such a declaration is not to be confused with third party certification of conformity, which may also be desirable.

## Appendix A Guidance on the use of bitumen-based coatings for cold application

### A.1 Safety instructions

Consult the safety instructions of the manufacturer before application and, especially, before spraying these materials.

NOTE Attention is drawn to the Health and Safety Executive Guidance Note GS5 "Entry into Confined Spaces" regarding the safe working in confined spaces.

### A.2 General properties

Like some other protective coatings referred to in BS 5493 and BS 6150, bitumen coatings are used to protect surfaces rather than to decorate them, their function being to exclude moisture or other corrosive agents. It is thus important that each coat is applied in a continuous manner, without holidays or "misses". Bitumen coatings have little power to inhibit corrosion. Hence, if ferrous surfaces are not adequately cleaned to be free from rust and mill-scale before these coatings are applied, under-rusting may occur with consequent failure of the film. They have good adhesion to most surfaces commonly found in building, e.g. ferrous metals, slightly etched galvanized iron and steel, concrete and brick, and will withstand moderate concentrations of acids and alkalis.

These bitumen coatings are neither intended to withstand hot conditions, as on boilers, smoke stacks, etc., for which special coatings should be obtained, nor to resist contamination with mineral oils or paint solvents, all of which conditions will cause softening of the film.

### A.3 Precautions

Provide adequate ventilation, particularly of closed vessels, while the material is being applied and until it is thoroughly dry. The use of air fed masks for personal ventilation is recommended. When painting the interiors of tanks, use a forced air supply to disperse the solvent and prevent residual solvent condensing on the coating and washing it off. Avoid naked lights in or near the tanks or cisterns during these periods. Use appropriate barrier creams and protective clothing to prevent skin sensitization. Skin should be thoroughly washed and clothing removed and cleaned as soon as possible after the work has been completed.

### A.4 Durability

The durability of bitumen coatings depends mainly upon a) the thickness of the film and b) the degree of exposure. It is important to apply the products liberally in a number of coats, as thick films give proportionately greater protection than thin ones, and to ensure that all areas of a surface are covered.

The degree of exposure largely controls the rate of deterioration of the film surface. Bitumen is sensitive to sunlight and other strong light, which quickly cause complete loss of gloss, followed later by a form of chalking. This is, however, confined to the surface and provided that the film is of adequate thickness it will continue to give protection. In situations protected from such attack, the gloss is maintained longer.

Crazing sometimes occurs with bitumen coatings but bitumen-coated ferrous metals are seldom subject to early corrosion from this cause.

### A.5 Thinning

Where thinning is necessary, e.g. as a first coat on very porous surfaces, only white spirit, in the case of class A coatings, or the manufacturer's recommended thinners should be used. In all cases thinning should be kept to a minimum for the type of use required.

### A.6 Primer

In order to prevent under-rusting on ferrous metals, a system of rust-inhibiting primer and bitumen coating is often advocated. Reference should be made to the bitumen-coating manufacturer. It is important to allow adequate time for the hardening of primers prior to the application of bitumen-based coatings. Lead-based primers and other primers containing toxic material are not to be used in conjunction with materials in contact with potable water.

### A.7 Preparation of surfaces

Establish that the substrate and the bitumen-based coating are compatible and prepare the substrate according to its type as follows.

- a) *Bare non-porous surfaces.* All dirt, including loosely adhering rust, mill-scale and grease should be removed.
- b) *Surfaces previously covered with bitumen coating.* All dirt, grease and loosely adhering bitumen coat should be removed by washing or other suitable means. Any bare patches of metal should be spot-primed with bitumen coating before the general coating is applied.
- c) *Porous surfaces.* All dirt and dust should be removed by thorough brushing and any loosely adhering flakes of material should be detached. Washing of porous surfaces is not usually satisfactory unless adequate time is given for the water to evaporate.
- d) *Other surfaces.* Reference should be made to the manufacturer of the bitumen-based coatings.



## A.8 Painting

All surfaces should be allowed to dry following the preparation. Painting during humid weather, or in other conditions giving rise to condensation, should be avoided. Further details of the establishment of conditions and appropriate application of coatings are given in a) to e) and in BS 6150.

a) *Application to non-porous surfaces.* A full coat should be applied by the appropriate method taking care to obtain a uniform and continuous film at the recommended spreading rate. Particular care should be taken to coat thoroughly all recesses, edges, joints, intersections of members, rivet and bolt heads and nuts.

No subsequent coat should be applied until the previous coat has dried thoroughly.

b) *Systems of bitumen-based coatings and corrosion-inhibitive primer on bare steel.* One or more coats of primer should be applied followed by at least two coats of bitumen-based coating.

NOTE The final coat of bitumen-based coating may, with advantage, be one which contains leafing aluminium as an additive to minimize the effect of sunlight (see A.4).

c) *Systems of bitumen-based coatings on cementitious surfaces.* These surfaces should be sealed with a thinned coating of type 1 bitumen-based coating (see A.5). If the original surface has a high degree of porosity a second thinned seal coating should be used. Two subsequent coats of non-thinned bitumen-based coating are usually necessary, all coatings being applied after ensuring the previous coating is thoroughly dry. The spreading rate of the material should be adjusted so as to give a satisfactory final film. If the original surface has a high degree of porosity, an additional thinned priming coat should be used.

If the surface is rough, as with some concrete surfaces, or irregular or jointed, as with brickwork, the method and coating should be agreed with the manufacturer.

d) *Use of bitumen-based coatings with other systems.* Bitumen-based coatings are unsuitable where it is desired to finish the work with many other types of paint, since bleeding of the bitumen through the top coat and crazing of the finish is likely to result. Where it is necessary to apply an oil paint over a bitumen coating these faults may be mitigated by the use of a barrier coat of a preparation made especially for this purpose.

e) *Application of material when used for coating drinking water tanks or cisterns.* Surfaces should be dry and cleaned free of mill-scale, rust and dirt. All surfaces, new or otherwise, should then be degreased immediately before coating. Two coats are recommended and on bare metal; brush application of the first coat is preferable. Full coats should be applied, particular care being taken to coat thoroughly all recesses, edges, rivet and bolt heads and nuts. In no case should a second coat be applied until the first coat is thoroughly dry and a period of 48 h should normally be allowed for this. Drying may be assisted materially by the provision of a forced draught. It is essential to use clean brushes or spray equipment; such tools contaminated with other types of bitumen paint or with tar paint are unsuitable.

After thorough drying of the two-coat system, and before being put into service, the tank or cistern should be filled with cold drinking water, and drained after not less than 4 h. If a taste is detected in this water, the flushing should be repeated. This procedure is necessary as a safeguard against initial contamination of the water because of entrapped solvent in the bitumen coat.

## Appendix B Methods of test for performance requirements

### B.1 Flash point

Test the coating in accordance with the method described in BS 3900-A8 or BS 3900-A13.

Record the results.

### B.2 Drying and over-coating times

#### B.2.1 Surface-dry time

Apply a single coat of the coating as described in Appendix C to a burnished nominal 150 mm × 100 mm steel panel. Test in accordance with BS 3900-C2.

Record the results after 4 h, for type 1 coatings, or after 8h, for type 2 coatings.

#### B.2.2 Over-coating time

Allow the coating obtained after the test of B.2.1 to dry for 24 h with free access of air at  $23^{\circ} \pm 2^{\circ} \text{C}$  and a relative humidity of  $50 \pm 5\%$ .

Overcoat with a second coat in accordance with C.3.

Inspect the film visually, by normal or corrected vision, during application and again after the over-coating has been allowed to dry for 24 h.

Record the observations.

**B.3 Finish**

Apply a single coat of the coating as described in Appendix C to a burnished nominal 300 mm × 300 mm steel panel to give the appropriate dry film thickness for its type given in C.2.

Inspect the resultant film visually by normal or corrected vision.

Record the observations.

**B.4 Protection against corrosion****B.4.1 Resistance to tap water immersion**

**B.4.1.1** Apply two coats as described in Appendix C to a burnished nominal 150 mm × 100 mm steel panel. Then 72 h after application, test in accordance with procedure A, Method 1 of BS 3900-G5:1976 using tap water and an immersion period of 4 days for type 1 material and 14 days for type 2 material.

Inspect the film visually by normal or corrected vision.

Record the observations.

**B.4.1.2** Remove the film with a non-corrosive paint remover complying with BS 3761.

Inspect the surface of the exposed metal by normal or corrected vision.

Record the observations.

**B.4.2 Resistance to artificial sea water immersion**

**B.4.2.1** Apply two coats as described in Appendix C to a burnished nominal 150 mm × 100 mm steel panel. Then 72 h after application, test in accordance with procedure A, method 1 of BS 3900-G5:1976. Use artificial sea water complying with 6.1 of BS 3900-F4:1968, with an immersion period of 4 days for type 1 material and 14 days for type 2 material.

Inspect the film visually by normal or corrected vision.

Record the observations.

**B.4.2.2** Remove the film with a non-corrosive paint remover complying with BS 3761.

Inspect the surface of the exposed metal by normal or corrected vision.

Record the observations.

**B.5 Bend resistance**

Apply a single coat as described in Appendix C to a burnished nominal 100 mm × 50 mm × 0.3 mm thick tinplate panel. Allow to dry for 7 days.

Test as described in BS 3900-E1, using type 1 apparatus. For type 1 coatings use a 6 mm mandrel. For type 2 coatings use a 10 mm mandrel.

Inspect the film visually by normal or corrected vision.

Record the observations.

**Appendix C Preparation and coating of test panels****C.1 Material and dimensions**

Use test panels of the material specified in BS 3900-A3 and of the specified dimensions.

**C.2 Preparation and coating**

Prepare the test panels in accordance with BS 3900-A3 and then coat by brushing, spraying, rolling or dipping as recommended by the manufacturer, to give a dry film thickness of  $35 \pm 5 \mu\text{m}$  for type 1 coatings or  $75 \pm 10 \mu\text{m}$  for type 2 coatings.

**C.3 Drying of test panels**

Dry the test panels in a vertical position at a temperature of  $23 \pm 2 \text{ }^\circ\text{C}$  and a relative humidity of  $50 \pm 5 \%$  for the specified time.

Allow the first coat to dry for 24 h before application of the second coat.

For the tests required in clause 8 coat the backs and edges of the panels with a protective paint system.



## Publication(s) referred to

BS 245, *Specification for mineral solvents (white spirit and related hydrocarbon solvents) for paints and other purposes.*

BS 2015, *Glossary of paint terms.*

BS 2523, *Specification for lead-based priming paints.*

BS 3761, *Specification for solvent-based paint remover.*

BS 3900, *Methods of test for paints.*

BS 3900-A1, *Sampling.*

BS 3900-A3, *Standard panels for paint testing.*

BS 3900-A8, *Test for flash/no flash (closed cup equilibrium method).*

BS 3900-A13, *Test for flash/no flash (rapid equilibrium method).*

BS 3900-C2, *Surface-drying test (ballotini method).*

BS 3900-E1, *Bend test (cylindrical mandrel).*

BS 3900-F4, *Resistance to continuous salt spray.*

BS 3900-G5, *Determination of resistance to liquids.*

BS 3900-H2, *Designation of degree of blistering.*

BS 5493, *Code of practice for protective coating of iron and steel structures against corrosion.*

BS 6150, *Code of practice for painting of buildings.*

BS 6920, *Suitability of non-metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of the water.*

BS 6920-1, *Specification.*

BS 6949, *Specification for bitumen-based coatings for cold application, excluding use in contact with potable water.*

EEC Directive 80/778/EEC. The quality of water intended for human consumption (also referred to under the reference EEC Council Directive of 15 July 1980 relating to the quality of water intended for human consumption [Official Journal of the European Communities L229 pp 11-29]).

UK Water Fittings Byelaws Scheme Information and Guidance Note No 5-01-02.

Health and Safety Executive Guidance Note GS5 — Entry into Confined Spaces (obtainable from HMSO).

---

# BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

## Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

## Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

## Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

## Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.